AFB™ 6680G


Avery Dennison AFB™ 6680G is a grey acrylic foam tape with general purpose acrylic adhesive. This firm, dense adhesive enables good lamination and maintains high internal strength on irregular substrates, even when surfaces are mismatched. Offers excellent longer term durability and internal strength, and is suitable for auto-dispensing by converters. Ideal for attachments in large domestic appliances, air-conditioners, housing lamination and nameplate or sign bonding. Suitable industry applications include manufacturing, construction and appliance assembly, including metal or plastic bonding with high internal strength. Suitable for office furniture and telecommunication mounting, decoration and TV frame mounting.

FEATURES:

- · Foam tape with viscoelastic acrylic foam carrier
- · Closed cell structure
- Acrylic adhesive system
- · Easy release polyethylene liner

BENEFITS:

- High adhesion combined with good shear absorbs shock and distributes stress evenly
- Good moisture, UV and high temperature resistance
- Uniform bonding performance
- Can help eliminate the need for mechanical fasteners, drilling or grinding and related clean-up for certain applications
- Polyethylene liner helps provide good moisture stability and easier converting with its high tear strength



CONSTRUCTION:

Liner:

Red Polyethylene Liner With Imprinted Avery Logo

Carrier and Adhesive:

Gray Acrylic Foam Core



AFB™ 6680G

SS

Adnesive Properties:		rypical values		
Thickness	ASTM D-3652	US Mils	MM's	Micron's (µm
Liner:		5.1	0.13	130
Carrier and Adhesive:		31.5	0.80	800
Total Caliper:		36.6	0.93	930
DEEL ADVISORY	T (M // //) DOTO 101	AOTH B ASSA		
PEEL ADHESION	Test Method(s): PSTC-101	, ASTM D-3330		
2 mil PET 90° 12 in /min	(305 mm / min)	Lbf / In		
Substrate	strate			N / 100 mm
SS	20 min dwell	7.8		137
2 mil PET 90° 12 in /min	(305 mm / min)			

9.7

Typical Values

170

DYNAMIC SHEAR	Test Method(s): ASTM D-100	Test Method(s): ASTM D-1002				
2 mil PET 0.5 in /min (12.7	mm / min)					
Substrate		Lbf / In²	kPa			
Liner	72 hr dwell	91.4	630			
NORMAL TENSILE Test Method(s): ASTM D-897						
Aluminum 2 in / min (50.8 mm / min) 1" sq (6.5 cm2)						
Substrate	·	Lbf / In²	kPa			
Aluminum	72 hr dwell	89.9	620			

STATIC SHEAR	Test Method(s): PSTC-101	, ASTM D-3330		
2 mil PET 1" sq (6.5 cm2)	500 g			
Substrate	Min to Fail			
SS	@ 90°C	> 10,000		
TEMPERATURES		° F	° C	

THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

APPLICATION TECHNIQUES

Long Term Temp (10,000 mins) Short Term Temp (240 mins)

- It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed

72 hr dwell

Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

STORAGE / SHELF LIFE

One year when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes. Avery Dennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2015 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Performance

Tapes

Asia Pacific Kunshan, China, NO. 618 Nanhe Road Kunshan Economic & Technological Zone China, 215335

Phone: +86 512 57155001 Fax: +86 512 57155059 Europe Tieblokkenlaan 1 B-2300 Turnhout Belgium

248 ° F

320 ° F

Phone: +32 (0)14 40 48 11 Fax: +32 (0)14 40 48 55 North America 250 Chester Street Painesville, Ohio 44077 USA

120 ° C

160 ° C

Phone: +1 866-462-8379 Fax: +1 888-358-4469